

# Radon Membrane Data Sheet



The Cordek Radon Membrane is a high performance gas membrane, for use in applications where resistance to radon gas is required as part of either a 'full' or 'basic' radon protection system.

For 'basic' radon protection the use of the Cordek Radon Membrane covering the entire footprint of the building, used in conjunction with the relevant accessories and system components should be sufficient. However if there is the requirement to provide 'full' radon protection, the additional use of a radon sump (please see Cordek Radon Sump data sheet) may be required – please contact the Cordek technical team for further assistance.

The Cordek Radon Membrane is generally used within construction applications, predominantly within the foundation design. It can also act as a high performance DPM.

## Key Features

- Economical method of providing radon protection to newly constructed buildings
- Provides additional damp proofing protection to the structure; no requirement for a separate DPM
- Robust membrane with a high resistance to damage and puncturing
- Complies with relevant industry codes and guidance including BR 211.

## Installation

In line with industry good practice, it is recommended that the Cordek Radon Membrane is jointed using conventional thermal (hot air/wedge) welding equipment or the Cordek jointing tape system, to provide adequate protection against radon gas and moisture ingress.

All laps and junctions within the membrane should be overlapped by a minimum of 150mm. Any penetrations within the membrane should be effectively sealed using the appropriate accessories and recommended details – please contact the Cordek technical team for further advice.

For further information on the full range of VOC & Ground Gas Protection, please contact the Cordek technical team on 01403 799600, [techsupport@cordek.com](mailto:techsupport@cordek.com) or consult our website at [www.cordek.com](http://www.cordek.com).

The membrane should be installed upon a suitably prepared, well compacted, level surface consisting of either a sand or concrete blinding of a minimum 50mm depth.

## Protection & Repair

Following installation, the Cordek Radon Membrane should be inspected for defects, holes, blisters, un-dispersed raw materials, and any sign of contamination by foreign matter prior to covering. The surface of the membrane should be clean at the time of inspection and free from debris.

Following installation of the membrane, the installer and specifier should assess the requirement for additional protection prior to the positioning of reinforcement and pouring of concrete upon it. If additional protection is required, then the Cordek Correx protection system should be used directly above the membrane.

If the membrane is damaged, it should be repaired by means of patching. Pinholes and small holes should also be repaired by patching. The patch should be made of the same barrier membrane and should extend at least 150mm outside the damaged area in order to ensure that the damaged area is covered completely. The patch should be prepared and either welded using a hot air gun or the Cordek jointing tape system to the main section of membrane.



**Product Data**

		Cordek Radon Gas Barrier
<b>Physical</b>	Colour	Red
	Thickness	0.3mm
	Tensile Strength	N <sup>1</sup> /50mm MD 9.9 N/mm <sup>2</sup> XD 9.9 N/mm <sup>2</sup>
	Elongation	% MD 500 XD 500
<b>Conformance section</b>	Accreditation	In process
<b>Performance</b>	Temperature Range	°C -40 to +70
	Gas Permeability - Radon	7.2 x 10 <sup>-12</sup> m <sup>2</sup> /s
	Installation	Cordek double sided jointing tape
<b>Logistics</b>	Sizes	4 x 25m
	Roll Weight	kg 27.6
	Pallet Quantity	rolls 40

**Storage & Handling**

Care should be taken when moving, transporting or handling to avoid damage, puncturing or tearing which can affect the performance of the membrane.

The membrane should be stored undercover so as to be protected from puncture, dirt, grease, moisture, sunlight and excessive heat. Damaged material should be quarantined and stored separately for repair or replacement. The rolls shall be stored on a prepared smooth dry surface (or fully boarded wooden pallets; note that

slatted pallets with sharp corners will damage the rolls) and stacked no more than two rolls high. The bottom rolls need to be chocked to prevent them from rolling.

Storage between 5°C and 30°C at 40-65% humidity under non-condensing conditions is recommended.

**Issued: 07/2016**

DISCLAIMER: Information contained within this 'Technical Data Sheet' is for guidance only, and it is intended for experienced construction industry workers. It contains summaries of aspects of the subject matter and does not provide comprehensive statements of construction industry practice. As conditions of usage and installation are beyond our control we do not warrant performance obtained. Please contact us if you have any doubt as to the suitability of application. The information provided within this document is based on data and knowledge correct at the time of printing.

**Cordek Ltd**

Spring Copse Business Park, Slinfold, West Sussex  
RH13 0SZ, United Kingdom

Telephone (+44) 1403 799600 Fax (+44) 1403 791718  
E-mail info@cordek.com

[www.cordek.com](http://www.cordek.com)

